

**ABSTRACT OF THE DISCLOSURE**

Two lengths of FRP rebar are formed into spirals and coupled at cross over locations to form a structure to be embedded into a cementitious material or covered in a cementitious material  
5 for repairing a form or in new construction.

## Support Structure and Method of Forming a Support Structure

### Field

5 This invention relates generally to the field of construction and more particularly to constructing or repairing large structures, such as but not limited to culverts, sewers and the like and provides environmentally friendly, holistic solution.

### Background

10

Concrete is very strong in compression, but relatively weak in tension. To compensate for this imbalance in concrete's behavior, reinforcement bars called rebars are cast into the concrete to carry the tensile structural load. Steel rebar has been commonly used for reinforcement.

15 More recently, reinforcement bar produced from continuous fiber, such as Basalt rebar has been found to be superior to steel in both pervious and non-pervious concrete. Basalt bar does not corrode.

20 In North America, steel rebar is typically used to reinforce concrete. Unfortunately, while the initial bond between reinforcing steel bars and concrete is strong, the steel can deteriorate within the concrete. A particular concern is rebar that spans a cold joint in the concrete. Cold joints can let in water and when steel rebar rusts it expands and this splits open the concrete letting yet more water in that causes even more rusting. This common concrete failure mode is called spalling.

25

In order to solve this problem, rebar can be galvanized, however there is a substantial monetary and environmental cost associated with galvanizing steel.

30 This invention uses a fiber reinforced polymer (FRP) rebar such as Basalt rebar which is sometimes referred to as "rock rebar". Basalt rebar is more environmentally stable than steel rebar and is comparable in cost and in some instances less than the cost of steel rebar.

Because Basalt rebar does not corrode, it was developed to be used in harsh environments such as sea walls and road bridges. One of the major problems the construction industry faces today is corrosion of reinforcing steel, which significantly affects the life and durability of concrete structures. Basalt rebar effectively obviates this problem.

5

Basalt rebar is made from a plentiful volcanic rock called Basalt. Magma in the earth's core is primary Basalt. The composition of Basalt rock may vary.

Relative to most common igneous rocks, Basalt compositions are rich in MgO and CaO and  
10 low in SiO<sub>2</sub> and the alkali oxides. Basalt generally has a composition of 45–52 wt% SiO<sub>2</sub>, 2–5 wt% total alkalis, 0.5–2.0 wt% TiO<sub>2</sub>, 5–14 wt% FeO and 14 wt% or more Al<sub>2</sub>O<sub>3</sub>.

Basalt fibers are manufactured in a single stage process by melting pure Basalt rock raw material. Basalt filaments are made by melting crushed volcanic basalt rock of a specific  
15 mineral mixture to 1,700 C° for 6 hours. The white hot material is subsequently drawn through platinum bushings and then cooled into fibers. The fibers cool into hexagonal chains resulting in a resilient structure substantially stronger than steel or fiberglass.

Basalt rebar is manufactured from continuous Basalt filaments and epoxy polymers, typically  
20 in a ratio of 80% Basalt fibers and 20% resin. To provide better adhesion to concrete the Basalt rebar is provided with a wound spiral thread around its periphery or the surface can be embedded with sand for better adhesion to concrete.

Basalt rebar is approximately 2.5 times stronger in tensile strength than series 60 steel rebar of  
25 the same diameter, and the tensile strength of continuous basalt fibers is about twice that of E-glass fibers and the modulus of elasticity is about 15-30% higher. Another advantage of Basalt fibers is that the thermal expansion coefficient is very close to that of concrete whereas steel is not. Hence, this lessens concrete cracking as temperatures vary. Basalt rebar is environmentally safe and is inert and non-toxic. The production process of Basalt fiber  
30 creates no environmental waste and it is non-toxic in use or recycling.

Basalt rebar weighs less than steel and its strength to weight ratio is 7.5 times greater than steel. Thus shipping costs are less than that of steel preserving its small environmental footprint compared to steel.

- 5 This invention provides a green solution to build structures or repair existing structures, such as sewers, culverts and pipes of various diameter and cross-section.

### Summary

- 10 In accordance with an aspect of this invention a method of forming a reinforcing structure onto a form, is provided, comprising:

providing a first length of FRP rebar adjacent to the form so that at least a portion of the FRP

rebar is arranged in a spiral pressing against the form at a plurality of locations;

- 15 providing a second length of FRP rebar adjacent to the first length of FRP rebar

so that a portion of the first and second lengths form spirals following different paths and conform to the form, wherein the first length and the second length of FRP rebar cross over each other at a plurality of locations and are coupled together at a plurality of said locations; and, covering at least a portion of the first and second lengths with a cementitious

- 20 material.

In accordance with another aspect of the invention, there is provided a reinforced structure comprising:

an initial form requiring reinforcement;

- 25 a first length of FRP rebar formed into a spiral and contacting the initial form;

a second length of FRP rebar formed into a second spiral and contacting the initial form;

- 30 wherein portions of the first length of FRP rebar criss-cross portions of the second length of FRP rebar at a plurality of locations; and wherein the first length of FRP rebar and second length of FRP rebar are coupled together at a plurality of said locations; and,

a cementitious material covering a substantial portion of the first length and second length of FRP rebar and some of the initial form.

In accordance with this invention there is provided a structure comprising:

- 5           a first length of FRP rebar shaped in a first spiral; and,  
          a second length of FRP rebar shaped in a second spiral, wherein the first and second lengths of FRP rebar formed in spirals cross over each other at a plurality of locations, and wherein some of those locations are coupled together.
- 10 In accordance with a preferred embodiment Basalt FRP is used.

### **Brief Description of the Drawings**

15 Exemplary embodiments of the disclosure will now be described in accordance with the drawings in which:

FIG. 1 is a prior art isometric view of a metal rebar frame.

FIG. 2 is a drawing in which FRP rebar is inserted into a culvert in preparation for spiraling.

FIG. 3 illustrates the start of a spiraling operation.

20 FIG. 4 illustrates two spiraled FRP rebars secured in position before grouting.

FIG. 4a is a cross-sectional view of the culvert and rebar of FIG. 4

FIG. 5 shows an alternative embodiment where the FRP rebar is spiralled onto the exterior of a form.

FIG. 5A is a cross-section of the drawing shown in FIG. 5.

25

### **Detailed Description**

Referring now to FIG. 1 a prior art structure formed of lengths of steel rebar 102 coupled with steel rebar hoops 104 is shown which forms a supporting structure upon which to apply a coat  
30 of cementitious material. The rebar structure 100 provides strength and support to the coating of cement applied overtop and lessens the likelihood of cracking. The rebar is standard steel

rebar which has the advantage of being highly ductile, but also has the disadvantage of easily corroding in the presence of water and being very heavy compared to FRP rebar. When steel rebar is used to repair old deteriorating culverts and sewers there is always a concern about water seeping into the concrete and adversely affecting the steel rebar. Building the structure

5 100 below is also quite labor intensive, especially when erecting a rebar cage in large culverts where many hoops 204 and parallel cross rebar members 102 are required. This is also done in a damp or wet environment where steel rebar is likely to rust even during the installation and repair.

10 FIGs. 2, 3 and 4 show an alternative embodiment of a structure, in accordance with the disclosure where a less labour intensive, system is erected in a very short amount of time and where two workers can erect the structure. No welding is required. The rebar used is fiber reinforced polymer (FRP) rebar which comes in many forms. It can be made of Basalt fibers, glass fiber, or carbon fiber. Notwithstanding, all of these FRP rebars have a similar

15 characteristic that lends to this invention. They have above adequate tensile strength, are lightweight, and do not corrode. Longer lengths of these FRP rebar types bend easily but are resilient and spring back from a bent form when released. Notwithstanding, if the bend radius is too small, the FRP will be damaged so care must be taken to ensure that the bend radius is suitable for the size and type of FRP rebar. The resilience of FRP rebar is not found in typical

20 steel rebar and is useful when positioning a length from a large diameter coils to form spiral. For example when steel rebar is bent, it remains bent. However, Basalt rebar when bent or coiled then fully released will spring back to a nearly straight form. If it is coiled and released from being held in a coil it will uncoil itself. Turning now to FIG. 2 two lengths of 8mm FRP rebar, 10A and 10B, preferably 8mm Basalt rebar is inserted into a culvert 30 in need of

25 repair. First ends of the rebar are fixed at 3'oclock and 9'o'clock positions at a far end of the culvert 30 while an operator holds two other ends of the Basalt rebar. The operator pushes both lengths of rebar 10A and 10B into the culvert with moderate the force and interlaces both lengths into two spirals. This is illustrated more clearly in FIGs. 3 and 4. It should be noted that by interlacing the lengths of FRP Basalt rebar they alternately cross over each other, 10A

30 crossing over 10B and 10B crossing over 10A. Plastic ties 20A and 20B secure the rebar and couple portions which cross over each other together. FIG. 4 shows a completed construction.

After the frame structure is completed cementitious material such as grout or concrete is applied over it, concealing the rebar and providing a supportive layer to repair the culvert. In an alternative embodiment, a grout tube having slits therein, follows one or both of the rebar lengths 10A and 10B and is coupled thereto. A skin in the form of a plastic cover may  
5 subsequently be applied over the rebar and grout tube after which grout is injected into the grout tube (not shown) and the grout fills the void between the culvert inner wall 30 and the plastic cover providing a sandwich of layers consisting of concrete reinforced with rebar support structure and a plastic wall.

10 FIG. 4A is cross section of the culvert 30 shown in Fig. 4 illustrating the rebar 10A and 10B covered in a layer of grout 30.

Although the FRP rebar 10A and 10B is shown supporting an inner wall of a culvert 30, Fig. 5 shows an alternative embodiment where a form consisting of a concrete grain silo 40 is  
15 wrapped in FRP Basalt rebar in two overlapping spirals before a layer of cementitious material is applied over the rebar.

As long as the FRP rebar is maintained in a spiral it is constantly under tension adding a small amount of tension against the form or culvert it is within. This is seen as an advantage, since  
20 in the construction industry compressive stresses are sometimes purposely introduced to produce prestressed concrete either by pre-tensioning or post-tensioning the steel reinforcement. The other advantage of the spiral being under tension is that it remains in place as long as the ends are held in a fixed position, so that it cannot unwind. This eases construction of two spiral lengths of FRP rebar within or upon a form. If rebar was limp, or  
25 overly stiff it would be difficult to form it into a spiral, however due to the nature of FRP rebar, it lends itself to being formed into a spiral conforming to the inside of a culvert and obviates the more complex construction shown in FIG. 1. It should be noted that although preferable to used two separate lengths of FRP rebar, it may be possible to use a single length where the middle is placed at one end of the culvert and the two lengths on either side of the  
30 middle overlap each other in spirals, where one overlaps the other in an alternating pattern.

## CLAIMS

What is claimed is:

- 5 1. A method of forming a reinforcing structure onto a form, comprising:  
providing a first length of FRP rebar adjacent to the form so that at least a portion of  
the FRP rebar is arranged in a spiral against the form at a plurality of locations;  
providing a second length of FRP rebar adjacent to the first length of FRP rebar  
such that a portion of the first and second lengths form spirals following different paths and  
10 conform to the form, wherein the first length and the second length of FRP rebar cross over  
each other at a plurality of locations and are coupled together at a plurality of said locations;  
and, covering at least a portion of the first and second lengths with a cementitious material.
- 15 2. A method as defined in claim 1 wherein the form is a pipe and wherein the first and second  
lengths of FRP rebar are disposed within the pipe adjacent the inner wall of the pipe.
3. A method as defined in claim 2, wherein the pipe is a culvert or sewer pipe and wherein the  
first and second lengths are separate lengths of basalt rebar.
- 20 4. A method as defined in claim 2 wherein the first and second lengths are intertwined so that  
the first length overlaps the second length at a plurality of locations and wherein the second  
length overlaps the first length at a plurality of other locations.
- 25 5. A method as defined in claim 4, where the first and second lengths of FRP rebar are Basalt  
rebar and are formed into a coil after being inserted into the interior of the pipe.
6. A method as defined in claim 4 wherein an angle formed between two overlapping lengths  
of the basalt rebar is within a range between 15 and 45 degrees.

7. A method as defined in claim 4, further comprising a spiral conduit conforming to the culvert or sewer pipe having an end for accepting grout and having openings therein for injecting grout into a plurality of regions about the basalt rebar lengths.
- 5 8. A method as defined in claim 4, where the basalt rebar includes a plurality of constituents.
9. A method as defined in claim 2, wherein the first and second lengths of basalt rebar are a contiguous single length of rebar.
- 10 10. A method as defined in claim 1 wherein the form has a rectangular, square, or circular cross-section.
11. a method as defined in claim 1 wherein the rebar Basalt fiber reinforced polymer reinforcing bar.
- 15 12. A method as defined in claim 8 wherein the Basalt rebar contains Basalt filament and epoxy polymer.
13. A method as defined in claim 1 further comprising:
- 20       applying a cladding, disposed over the first and second basalt rebar coils; and,  
          applying a cementitious material between the cladding and the form to encapsulate the rebar coils.
14. A reinforced structure comprising:
- 25 an initial form requiring reinforcement;  
a first length of FRP rebar formed into a spiral and contacting the initial form;  
a second length of FRP rebar formed into a second spiral and contacting the initial form;  
wherein portions of the first length of FRP rebar criss-cross portions of the second length of FRP rebar at a plurality of locations; and wherein the first length of FRP rebar and second
- 30 length of FRP rebar are coupled together at a plurality of said locations; and,

a cementitious material covering a substantial portion of the first length and second length of FRP rebar and some of the initial form.

15. A supporting structure comprising:

- 5 a first spiral of FRP rebar; and,  
a second spiral of FRP rebar, wherein portions of the first and second spirals of FRP rebar cross over each other, and wherein some of those portions are coupled together.

16. A supporting structure as defined in claim 15 wherein the FRP rebar is basalt rebar.

10

17. A supporting structure as defined in claim 15 further comprising a grout tube coupled to the one of the first and second spiral bars.

18. A supporting structure as defined in claim 15, including a grout tube wherein the grout  
15 tube is formed into a spiral and is coupled to one of the first and second spirals.

**Statement under 84.1 (b) of the Patent Rules**

The applicant believes that this application relates to a technology the commercialization of which would help resolve and mitigate the environmental impact of using steel rebar which  
5 corrodes and leads to concrete spalling and deterioration of thousands of miles of culvert in  
North America. It uses FRP rebar which is light-weight, non-toxic, non-corrosive and costs a  
fraction of steel rebar to ship to a site location and provides a configuration that requires very  
little to no machinery to install.

10